## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **LISTING OF CLAIMS:**

- (Withdrawn) A process for forming the strippable glass fiber wall covering according to Claim 16, said process comprising:
  - (a) providing a glass fiber fabric,
  - (b) forming a first dried coating on both sides of said glass fiber fabric that is applied from an aqueous dispersion comprising a starch and a polymeric latex binder, and
  - (c) subsequently forming a second dried coating on said first dried coating on one side only of said glass fiber fabric that is applied from an aqueous dispersion consisting essentially of a paraffin wax and a rheology modifier with said second dried coating being capable of aiding in the removal of the wall covering from the wall.
- 2. (Previously Presented) A wall covering according to Claim 17, wherein said glass fiber fabric is a woven fabric.
- 3. (Previously Presented) A wall covering according to Claim 17, wherein said glass fiber fabric is a nonwoven.

Attorney's Docket No. 7112 Application No. <u>09/827,855</u>

- 4. (Withdrawn) A process according to Claim 1, wherein the glass fiber fabric is supplied in roll form.
- (Previously Presented) A wall covering according to Claim 17, wherein said starch component of the first dried coating is potato starch.
- 6. (Previously Presented) A wall covering according to Claim 17, wherein said polymeric latex binder component of the first dried coating is an acrylic latex binder.
- 7. (Previously Presented) A wall covering according to Claim 17, wherein said first dried coating includes a cross-linking agent.
- 8. (Previously Presented) A wall covering according to Claim 7, wherein said cross-linking agent of the first dried coating is a zirconium cross-linker.
- 9. (Previously Presented) A wall covering according to Claim 17, wherein said first dried coating additionally includes pigment.
- 10. (Previously Presented) A wall covering according to Claim 9, wherein said pigment of the first dried coating is titanium dioxide.
- 11. (Withdrawn) A process according to Claim 1 wherein the aqueous dispersions of said first and second dried coatings are applied on a continuous process.

Attorney's Docket No. 7112 Application No. 09/827,855

Page 4

- 12. (Withdrawn) The process of Claim 1 wherein the drying of the glass fiber fabric in steps (b) and (c) is accomplished through the use of drying cylinders.
- 13. (Withdrawn) The process of Claim 1 wherein the drying of the glass fiber fabric in steps (b) and (c) is accomplished in air driers.
- 14. (Withdrawn) The process of Claim 1 wherein the application of said aqueous dispersions in steps (b) and (c) is accomplished through the use of a rotating screen applicator.
- 15. (Withdrawn) The process of Claim 1 wherein the applying of said aqueous dispersions in steps (b) and (c) is accomplished through the use of transfer rollers.
  - 16. (Canceled)
- 17. (Currently Amended) A strippable glass fiber wall covering comprising a glass fiber fabric impregnated and coated on both sides with a first dried coating comprising a starch and a polymeric latex binder and having applied thereon a second dried coating to only one of the coated sides, whereby the second dried coating consists essentially of a paraffin wax and a rheology modifier and serves as a separation layer that facilitates the removal of said wall covering from a substrate, wherein the starch is present in an amount ranging from about 10 to 70% by wt. and the polymeric latex binder is present in an amount ranging from about 20 to 80% by

Attorney's Docket No. 7112 Application No. <u>09/827,855</u>

Page 5

wt., based on the dried weight of the first coating, and wherein the paraffin wax is present in an amount ranging from about 80 to 99% by wt. and the rheology modifier is present in an amount ranging from about 1 to 20% by wt., based on the dried weight of the second coating.

- 18. (Canceled)
- 19. (Canceled)
- 20. (Previously Presented) The wall covering according to Claim 17, wherein the rheology modifier is an acrylic thickener, a polyurethane thickener or a cellulose thickener.